

## Technical Data Sheet

---

Issued March 2004

### EPON™ Resin 830

#### Product Description

EPON Resin 830 is a slightly higher molecular weight BPA liquid epoxy as compared to EPON 828. The resin itself is resistant to crystallization and also in blends with HELOXY™Modifiers. EPON Resin 830 is somewhat higher in viscosity than EPON Resin 828, although the viscosity is still easily handled. It provides greater reactivity when combined with most curing agents.

#### Application Areas/Suggested Uses

- Industrial floor toppings and grouting
- High build glaze, sealer or gel coats
- General purpose casting and encapsulation
- Base resin for dilution with Heloxy Modifiers

#### Benefits

- Slightly higher viscosity than standard liquid epoxy
- Very good resistance to crystallization
- Higher reactivity at room temperature
- Low color
- Good chemical resistance

#### Sales Specification

Property	Units	Value	Test Method/Standard
Weight per Epoxide	g/eq	190 – 198	ASTM D1652
Viscosity at 25°C	P	170 – 225	ASTM D445
Color	Gardner	1 max.	ASTM D1544

#### Typical Properties

Property	Units	Value	Test Method/Standard
Density at 25°C	lb/gal	9.7	ASTM D1475

### Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

### Packaging

Available in bulk and drum quantities.

### Contact Information

For product prices, availability, or order placement, call our toll-free customer service number at: 1-877-859-2800

For literature and technical assistance, visit our website at: [www.hexion.com](http://www.hexion.com)

© and ™ Licensed trademarks of Hexion Inc.

#### DISCLAIMER

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION,** except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

PDS-3943- (Rev.3/6/2015 11:23:39 AM)