



# Krytox™ FPG 182

## Performance Lubricants

Rust Preventive, High Performance, Wide Temperature Grease

## Product Information

Krytox™ FPG 182 is a smooth, buttery white grease. It has been specifically developed to operate over a wide temperature service range and in extreme chemical and vacuum conditions. It has exceptional performance as shown by its bearing life test that has over 7 times the life of similar products. It is a perfluoropolyether (PFPE)-based grease

thickened with a special high performance PTFE thickener, and has exceptional chemical and oxygen resistance. It is designed to operate under severe conditions, and can be used for bearings, gears, and as a lubricant for O-rings and elastomers.

### Properties of Krytox™ FPG 182

Property	Analysis	Method
Penetration at 25 °C (77 °F), mm <sup>-1</sup>		D217
Unworked	305	
Worked, 60 strokes	303	
Cone Oil Separation, 30 hr, 204 °C (399 °F), wt %	13	ASTM D6184
Rust Prevention	Pass	ASTM D1743
Copper Strip Corrosion	1b	FTM 5309
Four-Ball Wear Test, mm, 1200 rpm, 40 kgf load, 1 hr, 75 °C (167 °F)	1.33	ASTM D2266
Use Range	-80 °C (-112 °F) to 210 °C (410 °F)	
Four-Ball Extreme Pressure Weld	800+ kg	ASTM D2596
Vacuum Stability Test, 24 hr, 125 °C (257 °F), 10 <sup>-6</sup> torr		ASTM E595
Total Weight Loss (TWL), wt%	0.070	
Volatile Condensable Material (VCM), wt%	0.027	
Low Temperature Torque, g-cm		ASTM D1478
at -62 °C (-80 °F)		
Starting	1070	
Running, 1 hr	507	
at -73 °C (-99 °F)		
Starting	3250	
Running, 1 hr	1141	
LOX Impact Sensitivity, 100 mm, 20 drops	Pass	ASTM D2512
Evaporation Loss, % wt, 22 hr, 204 °C (399 °F)	0.07	ASTM D2595
Foreign Particles, Micron Range		FTM 3005
25-74 micron	45	
75 microns or larger	0	

*continued*

### Properties of Krytox™ FPG 182 (continued)

Property	Analysis	Method
Bearing Life, 10,000 rpm, 204 °C (399 °F)	5400+ hr	ASTM D3336
SRV Wear, 50 Hz, 200N, 50C, 120 min	699 µm ball scar/0.084 Friction coefficient	ASTM D5707
Wear at 5000 Cycles, 150 lb Load, mm	1.03	ASTM D2714 (mod)
Density, g/mL at 20 °C (68 °F)	1.94	
<b>Base Oil Characteristics</b>		
Kinematic Viscosity, cSt		ASTM D445
at 40 °C (104 °F)	138	
at 100 °C (212 °F)	37.57	
at -54 °C (-65 °F)	9256	
Viscosity Index	313	ASTM D2270
Pour Point	-72 °C (-98 °F)	ASTM D97
Vapor Pressure, torr, 20 °C (68 °F)	8 x 10 <sup>-11</sup>	

### Storage and Handling

Shelf life: Indefinite shelf life in unopened container. It is normal for oil to separate from grease during storage. Before use, knead tubes or stir larger containers to remix.

### Product Package

Krytox™ FPG 182 is available in 50 and 100 g syringes, 8 oz tubes, and 1.76 lb cartridges.



The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit [krytox.com](http://krytox.com) or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2016 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

C-10685 (6/16)